

PremiumColour ASLAN C 118 Soft

The opaque self-adhesive coloured film for long term applications

This coloured series with high opacity in high glossy quality is ideal for the use of durable and long-term applications outdoors. Thanks to its smooth and flexible material, the trimming of the dispensable film is easy and quick to manage and gives clear processing advantages with its improved adjustment for contours and shapes.

PremiumColour ASLAN C 118 Soft is ideal for computerised cutting of designs and lettering.

For any questions concerning special usage, for example with the use of translucent elastic cloth, please contact our technical advisory service:

+49 (0) 2204.708-80

Construction

face-film:	PVC (polymeric softeners)	
thickness:	~ 70 µm	
adhesive:	acrylic pressure adhesive	square quantity: ~ 20 g/m ²
release liner:	silicone cardboard	square weight: ~ 140 g/m ²

Characteristics

adhesive strength: (ASTMD-903)	immediately after 1 week	~ 7.5 N/25 mm ~ 12 N/25 mm
dimensional stability:	applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.45 %
chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkaline and salts.	
light proofness:	DIN 53 388	non-fade grade: 6-8 Woll- Scale
combustibility:	Stuck on aluminum, the film is self-extinguishing.	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
minimum durability:	7 years outdoors, with vertical exposure, in middle-European climate.	

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany ·

phone +49 (0) 22 04. 7 08-80 · **fax** +49 (0) 22 04. 7 08-50 ·

e-mail info@ASLAN-schwarz.com

www.ASLAN-schwarz.com

ASLAN 
EXPERTISE IN SELF-ADHESIVE FILMS

PremiumColour **ASLAN C 118 Soft**

Processing

printability:	The material is printable with solvent and eco solvent containing inks. (In case of inadequate drying of the printing inks the film will be sodded and the adhesive negatively affected.)
application:	Application dry or wet. If applied wet, a possible whitening of the adhesive occurs but will fade away after a couple of days depending on the weather. For a wet application we recommend the transfer liquid ASLAN TL10. For the application of fonts etc. we recommend our ASLAN application tapes respectively the ASLAN TMO.
gloss:	There can be matt areas on the surface of the high glossy film near the core of the roll. These may be caused by the silicon cardboard flipside, but will disappear after a short period of time and don't influence the print results.
storage life:	Before application the foils can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 07|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany ·

phone +49 (0) 22 04. 7 08-80 · **fax** +49 (0) 22 04. 7 08-50 ·

e-mail info@ASLAN-schwarz.com

www.ASLAN-schwarz.com

ASLAN® 

EXPERTISE IN SELF-ADHESIVE FILMS