

Sandblast 600 ASLAN S 62

600 µm stencil film for especially heavy duty sandblasting works on stone

This self-adhesive stencil film is ideal for heavy duty sandblasting works on rough and polished stone surfaces. Thanks to its thickness of 600 µm Sandblast 600 ASLAN S 62 has a high mechanical resistance. After the application it can be easily removed and leaves no coloured stains on polished stone.

For additional information please contact our technical advisory service:
+49 (0) 22 04. 7 08-80

Construction

| | | |
|-----------------------|------------------------------|--|
| face-film: | PVC (polymeric softeners) | |
| thickness: | ~ 600 µm | |
| adhesive: | acrylic pressure adhesive | square quantity: ~ 35 g/m ² |
| release liner: | silicone polyester liner | square weight: ~ 75 µm |

Characteristics

| | | |
|---|---|--|
| adhesive strength: (ASTMD-903) | immediately after 1 week | ~ 2,0 N/25 mm ~ 4,5 N/25 mm |
| dimensional stability: | applied onto metal surfaces after 48 hours stored at 70 °C | no longitudinal or lateral contraction |
| combustibility: | Stuck on aluminum, the film is self-extinguishing | |
| temperature: | application temperature: service temperature range: | min. 15°C -30 °C up to +80 °C |

ASLAN, Schwarz GmbH & Co. KG
Oberaue 2 · 51491 Overath · Germany
phone +49 (0) 2204.708 80 · **fax** +49 (0) 2204.708 50
e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN[®]
EXPERTISE IN SELF-ADHESIVE FILMS

Sandblast 600 ASLAN S 62

Processing

application:

Dry application only. Humidity, longer application processes and high temperatures increase the adhesive strength.

For the application of letterings etc. we recommend our application tape LowTackTape ASLAN TP 110 respectively the ASLAN TMO.

storage life:

Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 05|2016

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49 (0) 2204.708 80 • **fax** +49 (0) 2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN®
EXPERTISE IN SELF-ADHESIVE FILMS