



dorotape

Slip Resistance Information

RAPRA TEST REPORT SUMMARY

Dated : April 2002

SLIP RESISTANCE DETERMINATION OF SELF-ADHESIVE FLOORING FILM

PRODUCT NAME: ESSENTIAL FLOOR LAMINATE

EXPERIMENTAL DETAILS

Samples were tested in accordance with the following standards, except as otherwise noted. Tests were carried out on both dry and wet samples.

T.R.R.L Pendulum Tester

Testing was carried out in accordance with specification BS6677: Part1:1986 for the measurement of floor slip resistance utilising the RAPRA Four S Slider.

UK SLIP RESISTANCE GROUP LIMITS

Four S Pendulum Value

Potential for Slip

25 and below

HIGH

25 to 35

MODERATE

35 to 65

LOW

above 65

EXTREMELY LOW

RESULTS FOR ESSENTIAL FLOOR LAMINATE

Four S Pendulum Value

Potential for Slip

DRY 72

EXTREMELY LOW

WET 50

LOW

DISCUSSION

Test results show extremely low risk of slip when dry and low risk when wet. Results do not take into account "wear" over time and the condition of the many floor different floor surfaces for which the product may be applied.

Doro Tape (UK) Ltd
New Mill
Farndon Road
Market Harborough
Leicestershire
LE16 9NP

Tel: 01858 431642
Fax: 01858 466992
Email: sales@dorotape.co.uk