

GlassColour ASLAN CT 113

The transparent coloured film

This colour series is made for creative applications on signs and glass. It has brilliant colour effects when illuminated, as well as on white or reflecting backgrounds. Despite its high adhesive power after 24 hours, the film is easily removable.

The clear film is free of streaks and colour deficiencies.

By applying of one film over the other an unlimited number of colour nuances and blends can be obtained.

GlassColour ASLAN CT 113 is ideal for computerised cutting of designs and lettering's.

For any questions concerning special usage, for example with the use of translucent elastic cloth, please contact our technical advisory service:

+49 (0) 2204.708-80

Construction

face-film:	soft-PVC	
thickness:	~ 80 µm	
adhesive:	acrylic pressure adhesive, removable	square quantity: ~ 22 g/m ²
release liner:	silicone cardboard	square weight: ~ 140 g/m ²

Characteristics

adhesive strength: (ASTMD-903)	immediately after 1 week	~ 7.5 N/25 mm ~ 15 N/25 mm
dimensional stability:	applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.5 %
chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkaline and salts.	
light proofness:	DIN 53 388	non-fade grade: 6-8 (Woll-Scale)
combustibility:	stuck on aluminum, the film is self-extinguishing.	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
minimum durability:	3-5 years outdoors, with vertical exposure, in middle-European climate.	

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany ·

phone +49 (0) 2204. 7 08-80 · **fax** +49 (0) 2204. 7 08-50 ·

e-mail info@ASLAN-schwarz.com

www.ASLAN-schwarz.com

ASLAN 

EXPERTISE IN SELF-ADHESIVE FILMS

GlassColour ASLAN CT 113

Processing

application:

Application dry or wet. If applied wet, a possible whitening of the adhesive occurs but will fade away after a couple of days depending on the weather.

For a wet application we recommend the transfer liquid ASLAN TL10.
For the application of letterings e.g. we recommend our ASLAN Application Tapes respectively the ASLAN TMO.

gloss:

There can be matt areas on the surface of the high glossy film near the core of the roll. These may be caused by the silicon cardboard flipside, but will disappear after a short period of time and don't influence the print results.

storage life:

Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 09|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberaue 2 · 51491 Overath · Germany ·

phone +49 (0) 22 04. 7 08-80 · **fax** +49 (0) 22 04. 7 08-50 ·

e-mail info@ASLAN-schwarz.com

www.ASLAN-schwarz.com

ASLAN® 

EXPERTISE IN SELF-ADHESIVE FILMS